INTERNATIONAL JOURNAL OF ENGINEERING MANAGEMENT AND SOCIAL SCIENCES (IJEMSS)

e-ISSN : 3139-065X

www.ijemss.com

editor@ijemss.com

Vol. 01, Issue 1, May 2026, pp : 1-6

SUSTAINABLE CONCRETE USING INDUSTRIAL WASTE MATERIAL

[1]P Abhilash,

[1]Scientist,CSMRS,New Delhi,ORCID: **0000-0002-3767-7846**

ABSTRACT

The global construction industry accounts for approximately 8% of total CO2 emissions, with conventional Portland cement being the primary contributor. This article presents a comprehensive review of how industrial by-products — including fly ash, ground granulated blast-furnace slag (GGBS), silica fume, rice husk ash, and recycled aggregates — can effectively replace conventional concrete constituents. We examine the mechanical properties, durability, workability, and environmental performance of waste-incorporated concretes. Our findings demonstrate that strategic use of industrial waste materials can reduce CO2 emissions by 20 to 60 percent, lower production costs by 10 to 30 percent, and simultaneously improve long-term structural performance. The paper also addresses challenges in standardization, quality control, and large-scale adoption across developing and developed economies.

Keywords: sustainable concrete, fly ash, GGBS, silica fume, supplementary cementitious materials, green construction, industrial waste, circular economy

1. Introduction

Concrete is the most widely consumed construction material on Earth, with over 10 billion tonnes produced annually. At its core lies Portland cement, whose manufacture involves the calcination of limestone at temperatures exceeding 1,450 degrees Celsius. This energy-intensive process releases enormous quantities of carbon dioxide, positioning the cement industry as one of the leading industrial contributors to global greenhouse gas emissions.

As climate commitments tighten under frameworks such as the Paris Agreement and national net-zero targets, the construction sector faces urgent pressure to decarbonize. Industrial waste materials — historically treated as disposal problems — now represent a compelling opportunity. Rich in silica, alumina, and calcium oxides, many industrial by-products exhibit cementitious or pozzolanic properties that allow them to partially or fully substitute Portland cement clinker.

Beyond environmental benefits, the use of industrial waste in concrete can enhance certain mechanical and durability properties, reduce costs for manufacturers and end-users, and support the transition toward a circular economy. This article synthesizes global research across the most widely studied waste materials, examines real-world applications, and maps the path toward mainstream adoption.

2. Industrial Waste Materials in Concrete

A wide range of industrial by-products have been studied and implemented as supplementary cementitious materials (SCMs) or aggregate replacements. The following subsections detail the most significant categories.

2.1 Fly Ash

Fly ash is a fine powder recovered from the flue gases of coal-fired power plants. It is the most extensively used SCM globally, with annual production exceeding 750 million tonnes. Class F fly ash exhibits strong pozzolanic activity, reacting with calcium hydroxide released during cement hydration to form additional calcium silicate hydrate gel, the primary strength-bearing phase in concrete.

Research consistently demonstrates that replacing 20 to 30 percent of Portland cement with fly ash yields the following benefits:

INTERNATIONAL JOURNAL OF ENGINEERING MANAGEMENT AND SOCIAL SCIENCES (IJEMSS)

e-ISSN : 3139-065X

www.ijemss.com

editor@ijemss.com

Vol. 01, Issue 1, May 2026, pp : 1-6

- Reduces water demand by 5 to 10 percent due to the spherical particle morphology
- Lowers early-age heat of hydration, reducing the risk of thermal cracking in mass concrete
- Improves long-term compressive strength through continued pozzolanic reaction
- Enhances resistance to sulfate attack and alkali-silica reaction
- Reduces CO2 emissions by approximately 0.9 kg per kg of cement replaced

2.2 Ground Granulated Blast-Furnace Slag (GGBS)

GGBS is a glassy by-product of iron manufacturing, formed when molten slag is rapidly quenched with water or steam. Unlike fly ash, GGBS is a latent hydraulic material that reacts directly with water in the presence of an alkaline activator. Replacement levels of 30 to 70 percent are common in practice.

Concrete incorporating GGBS demonstrates markedly improved durability characteristics: reduced chloride ion permeability, making it ideal for marine and bridge structures; superior resistance to carbonation at high replacement levels; and a notably denser microstructure due to the refined pore system. The steel industry produces approximately 400 million tonnes of blast-furnace slag annually, a substantial fraction of which is suitable for GGBS production.

2.3 Silica Fume (Microsilica)

Silica fume is an ultra-fine amorphous silicon dioxide powder collected as a by-product of silicon metal and ferrosilicon alloy production. With particles approximately 100 times finer than cement and a high amorphous silica content of 85 to 98 percent, silica fume is among the most reactive pozzolans available. Typical addition rates are 5 to 10 percent by mass of cement.

The primary effects of silica fume inclusion are a dramatic reduction in pore size and porosity, increased compressive and flexural strength, and enhanced resistance to chemical attack. High-performance and ultra-high-performance concretes routinely rely on silica fume to achieve compressive strengths above 150 MPa.

2.4 Rice Husk Ash (RHA)

Rice husk ash is produced by the controlled combustion of rice husks, an agricultural residue abundantly available across Asia, Africa, and South America. When burned at temperatures between 550 and 700 degrees Celsius, RHA retains a highly porous, amorphous silica structure with a surface area rivaling silica fume. Global rice production generates over 150 million tonnes of husk annually, a largely underutilized resource in many developing nations.

Studies have shown that 10 to 20 percent replacement of cement with RHA improves compressive strength, reduces permeability, and boosts resistance to chloride ingress and acid attack. RHA offers a particularly attractive proposition for rural and low-income construction contexts where imported industrial materials are costly.

2.5 Recycled Concrete Aggregates (RCA)

Demolition waste constitutes a major fraction of the global solid waste stream, upward of 40 percent in many countries. Recycled concrete aggregates, produced by crushing demolished concrete structures, can substitute natural coarse aggregates. However, RCA typically carries a layer of old cement paste that increases porosity and water absorption, necessitating careful mix design adjustments.

Research indicates that up to 30 percent RCA replacement can achieve equivalent structural performance to conventional concrete when water-to-cement ratios and admixture use are optimized. Emerging techniques such as pre-soaking RCA, surface carbonation treatment, and the two-stage mixing approach are improving the reliability of RCA-based concrete.

3. Comparative Properties of Waste-Incorporated Concretes

INTERNATIONAL JOURNAL OF ENGINEERING MANAGEMENT AND SOCIAL SCIENCES (IJEMSS)

e-ISSN : 3139-065X

www.ijemss.com

editor@ijemss.com

Vol. 01, Issue 5, May 2026, pp : 1-6

Table 1 below summarizes the key performance characteristics of concrete incorporating various industrial waste materials, benchmarked against conventional Portland cement concrete:

Material	Replacement (%)	CO2 Reduction (%)	Compressive Strength	Cost Reduction (%)
Fly Ash (Class F)	20-40%	20-35%	Moderate to High (long term)	10-20%
GGBS	30-70%	40-60%	High (long term)	15-25%
Silica Fume	5-10%	5-10%	Very High	Variable
Rice Husk Ash	10-20%	10-20%	Moderate to High	8-18%
Recycled Aggregates	Up to 30%	15-25%	Moderate	5-15%
Ternary Blend	30-50% total	35-55%	High	15-30%

Table 1: Comparative performance of industrial waste materials as concrete constituents

4. Ternary and Quaternary Blend Systems

Rather than relying on a single SCM, contemporary research increasingly focuses on multi-component blends that exploit the complementary properties of different waste materials. Ternary systems combining two SCMs with Portland cement can overcome individual limitations and unlock synergistic benefits.

A well-studied ternary system pairs fly ash and silica fume: the coarser fly ash particles improve workability while the ultra-fine silica fume fills the voids between fly ash and cement particles, producing an exceptionally dense microstructure. Similarly, GGBS combined with RHA has shown excellent resistance to seawater exposure in coastal construction applications in Southeast Asia.

Key benefits of multi-component systems include:

- Extended cement replacement ratios up to 60 to 70 percent while maintaining or exceeding OPC performance
- Complementary particle size distributions that minimize void space and reduce paste volume
- Combined pozzolanic and latent hydraulic reactions providing both early and late strength gains
- Further reductions in embodied carbon with some ternary mixes achieving over 50 percent CO2 reduction versus OPC
- Enhanced resistance to multiple durability threats simultaneously including chloride, sulfate, and freeze-thaw

The optimization of ternary blends requires careful consideration of raw material availability, regional climate conditions, target performance specifications, and applicable building codes. Geopolymer concretes, which eliminate Portland cement entirely by relying on alkali activation of GGBS or fly ash, represent the logical endpoint of this trajectory, though their adoption is currently limited by consistency and curing challenges.

5. Environmental and Economic Impact Assessment

5.1 Carbon Footprint Reduction

The environmental case for waste-incorporated concrete is compelling. Life cycle assessment studies consistently demonstrate significant reductions in global warming potential compared to OPC-based concrete. A 2023 meta-analysis of 120 LCA studies found that fly ash concrete reduces global warming potential by 18 to

INTERNATIONAL JOURNAL OF ENGINEERING MANAGEMENT AND SOCIAL SCIENCES (IJEMSS)

e-ISSN : 3139-065X

www.ijemss.com

editor@ijemss.com

Vol. 01, Issue 5, May 2026, pp : 1-6

36 percent at 30 percent replacement, GGBS concrete reduces it by 38 to 62 percent at 50 percent replacement, and geopolymer concrete reduces it by 40 to 80 percent depending on activator choice.

Beyond CO2, waste utilization in concrete eliminates the energy and land costs associated with landfilling or stockpiling industrial by-products. In India alone, approximately 200 million tonnes of fly ash are generated annually, with disposal posing serious threats to groundwater quality and land use near thermal power plants.

5.2 Economic Considerations

The economic viability of sustainable concrete depends heavily on the regional cost of raw materials, waste availability, transportation logistics, and regulatory frameworks. In markets where carbon pricing or landfill taxes are in effect, the economic case for SCM incorporation is strengthened further.

In India, China, and Southeast Asia where coal power remains prevalent, fly ash is available at minimal cost and in enormous quantities. European construction markets benefit from abundant GGBS supply tied to domestic steel production. The global silica fume market, while smaller, is driven by demand for high-performance concrete in infrastructure projects.

5.3 Social and Circular Economy Dimensions

The integration of industrial waste into concrete production supports circular economy principles by converting liabilities into resources. Steel plants, power utilities, and silicon manufacturers benefit from revenue generated through SCM sales rather than waste disposal costs. Construction firms benefit from material cost savings and green building certifications such as LEED, GRIHA, and BREEAM that enhance project value.

Furthermore, the development of localized waste valorization supply chains creates employment opportunities in waste processing, quality testing, and logistics, an important consideration in developing economies where both construction demand and industrial waste generation are growing rapidly.

6. Challenges, Standards, and Future Directions

6.1 Standardization and Codes

One of the most significant barriers to widespread adoption of waste-incorporated concrete is the patchwork of national and international standards governing SCM use. While ASTM C618 in the USA, IS 3812 in India, BS EN 450 in Europe, and AS 3582 in Australia provide frameworks for fly ash and GGBS, many emerging waste materials including RHA, bottom ash, and copper slag lack harmonized specifications. This creates uncertainty for designers, contractors, and certifiers.

Regulatory bodies including the American Concrete Institute, fib, and the European Committee for Standardization are actively updating codes to incorporate broader SCM allowances and performance-based specifications. Performance-based approaches, which evaluate concrete against durability indicators rather than prescribing fixed mix proportions, offer greater flexibility for innovative formulations.

6.2 Quality Variability and Quality Control

The chemical composition and physical properties of industrial waste materials can vary significantly between sources, seasons, and production processes. Coal-fired power plants burning different fuel blends produce fly ash of varying reactivity and fineness. Inconsistent quality imposes greater testing burdens and can lead to conservative mix designs that underutilize the potential of SCMs.

Advances in rapid characterization techniques including X-ray fluorescence, laser diffraction particle sizing, and the R3 calorimetry test for reactivity are enabling faster, more reliable quality assurance. Artificial intelligence and machine learning models are increasingly being applied to predict concrete performance from raw material inputs, accelerating the mix design process.

INTERNATIONAL JOURNAL OF ENGINEERING MANAGEMENT AND SOCIAL SCIENCES (IJEMSS)

e-ISSN : 3139-065X

www.ijemss.com

editor@ijemss.com

Vol. 01, Issue 5, May 2026, pp : 1-6

6.3 Technological Frontiers

Emerging research directions are pushing the boundaries of what is achievable with industrial waste in concrete:

- Carbon capture and storage integrated with cement production to produce low-carbon clinker alongside SCM blending
- Nano-engineered SCMs through processing fly ash or RHA to nano-particle size to dramatically increase surface area and reactivity
- Alkali-activated and geopolymer concretes using 100 percent industrial waste binders, eliminating Portland cement
- 3D-printed concrete using SCM-rich pastes, enabling complex structural geometries with minimal material waste
- Bio-mineralization techniques that use microbial activity to strengthen RCA surfaces and reduce porosity
- Digital material passports tracking the provenance, composition, and performance history of waste-derived concrete ingredients

6.4 Policy and Industry Recommendations

Accelerating the transition to sustainable concrete requires coordinated action across government, industry, and research institutions. Key recommendations include:

- Governments should implement mandatory minimum SCM content requirements for publicly funded infrastructure projects
- Carbon taxes and landfill levies should explicitly price the benefit of waste valorization versus disposal
- Construction standards bodies should fast-track performance-based specification frameworks that welcome novel SCMs
- Research funding should prioritize pilot-scale demonstration projects in diverse climatic and structural contexts
- Industry consortia should develop shared quality certification platforms to reduce testing duplication
- Engineering education curricula should integrate sustainable concrete design as a core competency

7. Conclusion

The substitution of industrial waste materials for conventional Portland cement and natural aggregates represents one of the most impactful strategies available to the construction industry for reducing its environmental footprint. Fly ash, GGBS, silica fume, rice husk ash, and recycled aggregates each bring distinct advantages, and their intelligent combination in ternary and geopolymer systems opens pathways to concrete that is simultaneously stronger, more durable, lower in cost, and dramatically lower in embodied carbon.

The evidence reviewed in this article demonstrates that sustainable concrete is not a niche or experimental proposition. It is a mature, commercially available technology with decades of field performance data across diverse applications. The principal barriers to scaling are regulatory inertia, material quality variability, and knowledge gaps in the construction value chain, all of which are addressable through targeted policy, investment, and education.

As the world races to decarbonize its infrastructure and manage mounting volumes of industrial waste, sustainable concrete offers a rare convergence: an environmental imperative that is simultaneously an economic opportunity. The construction industry that embraces this transition earliest will be best positioned for a future shaped by carbon accountability, resource scarcity, and climate resilience.

INTERNATIONAL JOURNAL OF ENGINEERING MANAGEMENT AND SOCIAL SCIENCES (IJEMSS)

e-ISSN : 3139-065X

www.ijemss.com

editor@ijemss.com

Vol. 01, Issue 5, May 2026, pp : 1-6

References

1. Mehta, P.K. & Monteiro, P.J.M. (2014). Concrete: Microstructure, Properties, and Materials (4th ed.). McGraw-Hill Education.

2. Lothenbach, B., Scrivener, K. & Hooton, R.D. (2011). Supplementary cementitious materials. Cement and Concrete Research, 41(12), 1244-1256.

3. Habert, G. et al. (2023). Environmental impacts and decarbonization strategies in the cement and concrete industries. Nature Reviews Earth & Environment, 4, 259-276.

4. ASTM C618-22 (2022). Standard Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete. ASTM International.

5. Provis, J.L. & van Deventer, J.S.J. (2014). Alkali Activated Materials: State-of-the-Art Report, RILEM TC 224-AAM. Springer.

6. Kumar, S. & Sharma, R. (2023). Rice husk ash in sustainable concrete: A global review of mechanical and durability properties. Construction and Building Materials, 372, 130821.

7. Brundtland Commission (1987). Our Common Future. World Commission on Environment and Development, Oxford University Press.

8. World Cement Association (2024). Sustainability Progress Report 2024. WCA Publications, London.